

# Which SIVIC® for which property?

|                | NBR/PVC Ratio           | ACN content (%) | ML(1+4)100°C <sup>(1)</sup> | Fuel and Oil Resistance | Low temperature flexibility | Abrasion Resistance | Processability | Ozone Resistance <sup>(6)</sup> |
|----------------|-------------------------|-----------------|-----------------------------|-------------------------|-----------------------------|---------------------|----------------|---------------------------------|
| SIVIC® 2200    | 75/25                   | 30              | 62                          | ★                       | ★★★★★                       | ★★★★                | ★★★★           | ★★★★★                           |
| SIVIC® 2870 LV | 70/30                   | 28              | 65                          | ★                       | ★★★★                        | ★★                  | ★★★★           | ★★★★★                           |
| SIVIC® 2870    | 70/30                   | 28              | 75                          | ★                       | ★★★★                        | ★                   | ★★             | ★★★★★                           |
| SIVIC® 2870 HV | 70/30                   | 28              | 80                          | ★                       | ★★★★                        | ★★★★★               | ★              | ★★★★★                           |
| SIVIC® 3470    | 70/30                   | 34              | 68                          | ★★                      | ★★                          | ★                   | ★★★★           | ★★★★★                           |
| SIVIC® 3470 HV | 70/30                   | 34              | 50 <sup>(2)</sup>           | ★★                      | ★★                          | ★★★★                | ★              | ★★★★★                           |
| SIVIC® N 3970  | 70/30                   | 39              | 55 <sup>(2)</sup>           | ★★★                     | ★                           | ★★                  | ★              | ★★★★★                           |
| SIVIC® N 4570  | 70/30                   | 45              | 55 <sup>(2)</sup>           | ★★★★★                   |                             | ★                   | ★              | ★★★★★                           |
| SIVIC® N 2860  | 60/40/10 <sup>(3)</sup> | 28              | 65                          | ★★                      | ★                           | ★                   | ★★★★★          | ★★★★★                           |
| SIVIC® N 530   | 50/50                   | 33              | 60 <sup>(2)</sup>           | ★★★                     |                             | ★★                  | ★              | ★★★★★                           |

SIVIC® Trademark SIDIAC

|                  | NBR/PVC/<br>plasticizer<br>Ratio | ACN content (%) | ML(1+4)100°C <sup>(1)</sup> |
|------------------|----------------------------------|-----------------|-----------------------------|
| SIVIC® N 2710 N  | 60/40/70 <sup>(4)</sup>          | 33              | 22                          |
| SIVIC® N 2710 PF | 60/40/70 <sup>(5)</sup>          | 33              | 25                          |
| SIVIC® 5200 B    | 80/20/50 <sup>(5)</sup>          | 33,5            | 27                          |

(1) Unmassed – ISO 289-1

(2) MS(1+4) 100°C

(3) Oil extended with 10 phr of DOTP

(4) Oil extended with DINP

(5) Oil extended with phthalate free plasticizer

(6) Ozone resistance on SIDIAC's white standard compound  
200 ppm – 100% elongation – 55% relative humidity – 40°C